



ProPel 4600

MULTI-RANGE WATER-REDUCING ADMIXTURE FOR CONCRETE

DESCRIPTION:

ProPel 4600 is a normal setting multi-range water-reducing admixture for concrete. It is designed to facilitate the placing and finishing of concrete that is highly flowable and workable for extended periods of time with normal setting characteristics.

By varying the dosage rate, **ProPel 4600** can be used as a normal, mid-range and high-range water-reducing admixture.

ADVANTAGES:

- Improves the quality of concrete by decreasing water-cementitious ratio
- Increases early and ultimate compressive and flexural strengths
- Improves durability and reduces permeability
- Reduces water content needed for a given workability
- Reduces excess surface bleeding
- Reduces cracking, creep, and shrinkage
- Improves concrete viscosity, reduces segregation and increases cohesiveness
- Improves paste quality, concrete finishability and workability
- Improves pumpability of concrete



- Reduces “bug-holes” and improves formed surfaces
- Maintains slump life during extended mixing times
- Improves bond strength to the steel

DOSAGE RATE:

ProPel 4600 is recommended for use at a dose of 7 to 20 fluid ounces per 100 pounds of cementitious to meet the requirements of ASTM C 494 Type A water-reducing and Type F high-range water-reducing admixture.

Because local job conditions and materials vary, contact your local Pro Mix technical service representative for further assistance if using this product outside recommended dosage ranges (such as silica fume) or when combining with other admixtures.

SPECIFICATIONS:

Conforms to:

ASTM C 494 Types A and F

AASHTO M 194 Types A and F

CRD C 87 Types A and F

All other Federal and State specifications

COMPATIBILITY:

ProPel 4600 is compatible with all types Portland cement, class C and F fly ash, silica fume, GGBFS, fibers, approved air entraining, and water-reducing admixtures. **ProPel 4600** can be used in white, colored, and architectural concrete. For best results, each admixture must be introduced separately into the concrete mix.

MIX PERFORMANCE DATA:

517 lbs. (307 kg) of Type I cement per cubic yard (cubic meter)

Air Content: 5.0%

Slump Plain: 1.0 inches (25.4 mm)

Slump after water: 7.5 inches (191 mm)

Slump after (12oz/cwt) **ProPel 4600**

7.0 inches (178 mm)

TECHNICAL NOTE:

ProPel 4600 does not contain calcium chloride or any chloride-based components.


It will not promote or contribute to corrosion of reinforcing steel in concrete.

ProPel 4600 conforms to the minimum chloride ion limits published by current construction industry standards.

PACKAGING:

55-gallon drums, 275-gallon totes, and bulk delivery

Compressive Strength:



DIRECTIONS:

ProPel 4600 should be added with the initial mixing water or incorporated with the final water at the end of the batch sequence..

STORAGE:

ProPel 4600 may freeze at temperatures below 35 F (2 C). Although freezing does not harm **ProPel 4600**, precautions should be taken to protect it from freezing. If it should freeze, thaw at 45 F and reconstitute with mechanical agitation. **Do Not Use Pressurized Air For Agitation.**

SHELF LIFE:

18 months

PRO MIX Technologies warrants its products to be free from defects in material and manufacture. There are no other warranties by PRO MIX Technologies of any nature whatsoever, expressed or implied. This information is based on data and knowledge believed to be true and accurate at time of publication and is offered as a resource for the users of our products. PRO MIX Technologies assumes no liability in the use of this information and does not warranty the results obtained for any application. PRO MIX Technologies shall not be liable for damages of any sort, from the use or results of this product and shall not be responsible for conditions outside its control, including but not limited to, other materials, design, inspection, workmanship and field conditions. No statement, recommendation, or other information is intended to infringe on any patent or copyright held by others.