

PLASTIMIX 700

MID-RANGE WATER-REDUCING ADMIXTURE FOR CONCRETE

DESCRIPTION:

PLASTIMIX 700 is a ready to use aqueous solution of complex compounds which enhance the performance of plastic and hardened concrete. **PLASTIMIX 700** is manufactured under rigid quality control measures to provide uniform, reliable results.

USES:

PLASTIMIX 700 is recommended for concrete mixes where improved workability, pumpability and finishability is desired while maintaining or reducing the w/cm ratio. **PLASTIMIX 700** provides long “slump life” combined with uniform, normal set times. **PLASTIMIX 700** is often used to improve early and ultimate concrete strength performance.

ADVANTAGES:

- Provides increased slump, flowability and workability without increased water content and without segregation
- Improves concrete quality by reducing the water-cement ratio for a given degree of workability
- Provides single product solution to normal, mid and high-range water-reducing requirements
- Improves concrete finishability and surface quality



- Provides lubrication and enhances pumpability, including lightweight aggregate mixes
- Improves manufactured sand mixes
- Improves cement hydration/utilization resulting in more p.s.i. per lb. of cement
- Provides uniform, normal set, including GGBF (slag) and fly ash mixes.
- Increases early and ultimate strengths
- Reduces cracking and shrinkage
- Reduces concrete permeability
- Improves concrete durability

DOSAGE RATE:

PLASTIMIX 700 is recommended for use at a dosage rate of 4 to 14 fluid ounces per 100 pounds (260 to 1040 ml per 100 kg) of cement.

Because local job conditions vary, please contact your local Pro Mix sales representative for further assistance if using outside recommended dosage ranges.

SPECIFICATIONS:

Conforms to ASTM C 494 Type A and F
ASTM C-1017 Type 1
AASHTO M 194 Type A and F
CRD C 87 Type A and F

TECHNICAL NOTE:

PLASTIMIX 700 does not contain any purposely added calcium chloride or other chloride based components. It will not promote or contribute to corrosion of reinforcing steel in concrete.

STORAGE:

PLASTIMIX 700 may freeze at temperatures below 32 F (2 C). Although freezing does not harm **PLASTIMIX 700**, precautions should be taken to protect it from freezing. If it should happen to freeze, thaw and reconstitute with mechanical agitations. **Do Not Use Pressurized Air For Agitation.**

COMPATIBILITY:

PLASTIMIX 700 is compatible with all types of Portland cement, class C and F fly ash, slag, microsilica, calcium chloride, fibers and approved air entraining, accelerating, retarding, and super plasticizing admixtures. Field evaluations to determine proper air entrainment dosage rates are suggested when using **PLASTIMIX**. It may be possible to reduce the air entraining admixture dosage rate to achieve the desired air content of the concrete mix. For best results, each admixture must be dispensed separately into the concrete mix.

PACKAGING:

55-gallon drums and bulk deliveries.

PRO MIX Technologies warrants its products to be free from defects in material and manufacture. There are no other warranties by PRO MIX Technologies of any nature whatsoever, expressed or implied. This information is based on data and knowledge believed to be true and accurate at time of publication and is offered as a resource for the users of our products. PRO MIX Technologies assumes no liability in the use of this information and does not warranty the results obtained for any application. PRO MIX Technologies shall not be liable for damages of any sort, from the use or results of this product and shall not be responsible for conditions outside its control, including but not limited to, other materials, design, inspection, workmanship and field conditions. No statement, recommendation, or other information is intended to infringe on any patent or copyright held by others.