



## OptiFinish-A758

### *VISCOSITY MODIFYING ADMIXTURE FOR CONCRETE*

#### **DESCRIPTION:**

**OptiFinish-A758** is a *viscosity modifying admixture* (VMA) designed to enable the production of self-compacting concrete. When added to the mix, concrete treated with **OptiFinish-A758** is more stable and resistant to segregation.

#### **ADVANTAGES:**

- Increases the viscosity and cohesiveness of the concrete mix
- Reduces concrete bleed water
- Reduces segregation in high water-cementitious and high slump mixes
- Aids in concrete mix stability with gap-graded aggregates
- Can be introduced at the batch plant or jobsite
- Enables the production of self-compacting concrete
- Normal setting characteristics throughout the dosage range
- Enhances the appearance of finished surfaces
- Easy to dispense

#### **APPLICATIONS:**

- Lean concrete mixes with minimum cementitious contents
- Harsh concrete mixes containing gap-graded aggregates and manufactured sands
- Highly fluid self-consolidating concrete mixes that require the use of a viscosity modifier to eliminate segregation.
- Mixes requiring reduction or elimination of bleed water.

#### **DOSAGE RATE:**

OptiFinish-A758 is recommended for use at a dose of 1 to 15 fluid ounces per 100 pounds (65 to 980 ml per 100 kg) of cementitious materials for most applications. Because local job conditions, materials, and applications vary, this product may require dosages outside the recommended dosage range.

#### **PERFORMANCE DATA:**

##### **Compressive Strengths:**

**OptiFinish-A758** has little effect on the compressive strength of the concrete. If a lower water-cementitious ratio or higher compressive strength is necessary, the use of additional high-range water reducer, such as **ProPel XL25** is recommended.

##### **Bleed Water:**

Bleed water is significantly reduced and may be eliminated in concrete mixes, neat mixes, and grout mixes.

##### **Slump:**

A slight decrease in slump should be expected after the addition of OPTIFINISH-A758 due to the increase in viscosity of the mix. An additional dose of high-range water reducer may be necessary to meet specified slump for placement. Slump retention will be similar to normal concrete mixes.

##### **Set Time:**

**OptiFinish-A758**, when used within the recommended dosage range, has very little effect on set time.

### **Mixing:**

**OptiFinish-A758** should be incorporated into the mix either with the initial mix water or after all other ingredients have been added and completely mixed. **OptiFinish-A758** can be added at the batch plant or jobsite.

### **Packaging:**

55-gallon drums, 275-gallon tote tanks, and bulk delivery.

PRO MIX Technologies warrants its products to be free from defects in material and manufacture. There are no other warranties by PRO MIX Technologies of any nature whatsoever, expressed or implied. This information is based on data and knowledge believed to be true and accurate at time of publication and is offered as a resource for the users of our products. PRO MIX Technologies assumes no liability in the use of this information and does not warranty the results obtained for any application. PRO MIX Technologies shall not be liable for damages of any sort, from the use or results of this product and shall not be responsible for conditions outside its control, including but not limited to, other materials, design, inspection, workmanship and field conditions. No statement, recommendation, or other information is intended to infringe on any patent or copyright held by others.